

8219w-6.5



2014000335Z



检测
CNAS L0891



(2014)国认监认字(152)号

检 验 报 告

TEST REPORT

No.: WR34611

产品名称：电梯用钢丝绳

Product Name: Steel wire ropes for lifts

委托单位：天津高盛钢丝绳有限公司

Entrusting Unit: Tianjin Goldsun Wire Rope Ltd.

检验类别：委托检验

Testing Sort: Entrusting test

国家金属制品质量监督检验中心
China National Steel Wire Products
Quality Supervision & Testing Center






国家金属制品质量监督检验中心检验报告

Test Report of China National Steel Wire Products Quality Supervision & Testing Center

WR34611

共 2 页第 1 页 Page: 1/2

委托单位 Client	天津高盛钢丝绳有限公司 Tianjin Goldsun Wire Rope Ltd.		
生产单位 Manufacturer	天津高盛钢丝绳有限公司 Tianjin Goldsun Wire Rope Ltd.		
产品名称 Product Name	电梯用钢丝绳 Steel wire ropes for lifts		
结构规格 Construction & Size	6.5 8×19W-IWRC 1570 U sZ		
检验类别 Test Sort	委托检验 Entrusting Test	样品数量 Sample Number	1 根 1pcs
抽样方法 Sampling Method	寄样 Posting	到样日期 Arrival Date	13/12/2014
样品特征 Sample Facies	无明显外观缺陷 No visible defects	委托人 Entrusting person	刘震 Liuzhen
检验依据 Reference of Test	ISO 4344: 2004 《电梯用钢丝绳-最低要求》及技术要求 ISO 4344: 2004 Steel wire ropes for lifts—Minimum requirements & specification		
检验项目 Test Item	钢丝绳直径 Diameter of steel wire rope: 1. 无载荷 No load, 2. 5%最小破断拉力 5% of minimum breaking force, 3. 10%最小破断拉力 10% of minimum breaking force; 4. 钢丝绳椭圆度 Ovality of steel wire rope, 5. 钢丝绳平均直径偏差 Average diameter variation of steel wire rope, 6. 钢丝绳捻距 Lay pitch of steel wire rope, 7. 钢丝绳破断拉力 Breaking force of steel wire rope.		
检验结论 Test conclusion	委托检验 7 项, 共检 7 项, 合格 7 项。 Entrusting test amount 7 items, tested, 7 items up to the standard. 送检样品所检检验项目符合 ISO4344: 2004 标准及技术要求。 The above items of the sample are conformable with ISO4344: 2004 & specification.		
备注 Remarks	签发日期 Date of issue: 2014.12.16 空白 Blank		

批准 Approved by:  审核 Reviewed by:  编制 Compiled by: 



质量
专用

国家金属制品质量监督检验中心检验报告

Test Certificate of China National Steel Wire Products

Quality Supervision & Testing Center

WR34611

共 2 页第 2 页 Page:2/2

检验项目 Test item		标准值 Required	检验值 Actual	单项判定 Judgment
钢丝绳直径 Diameter of steel wire rope (mm)	无载荷 No load	≤ 6.70	6.62	合格 Conformity
	5%最小破断拉力 5% of minimum breaking force	≥ 6.50	6.52	合格 Conformity
	10%最小破断拉力 10% of minimum breaking force	≥ 6.44	6.46	合格 Conformity
钢丝绳椭圆度 (%) Ovality of steel wire rope (%)		≤ 4	0.6	合格 Conformity
钢丝绳平均直径偏差 (%) Average diameter variation of steel wire rope (%)		≤ 3	0.2	合格 Conformity
钢丝绳捻距 (mm) Lay pitch of steel wire rope (mm)		≤ 43.88	41.67	合格 Conformity
钢丝绳破断拉力 (kN) Breaking force of steel wire rope (kN)		≥ 31.5	33.5	合格 Conformity

